



**American Rambouillet Sheep Breeders Association**

Fiber Diameter		Fiber Diameter		Fiber Diameter		Fiber Diameter	
Lot #	um	Lot #	um	Lot #	um	Lot #	um
1	18.99	52	23.66	107	24.65	152	22.22
2	19.99	53	26.88	108F	22.14	153	22.93
3F	23.00	54	29.93	109F	22.48	154	25.19
4	24.36	55	27.75	110F	22.31	155	26.13
5F	26.32	56F	25.03	111	27	156	27.74
6F	20.91	57	23.64	112	28.62	161F	23.05
7	23.75	58	24.31	113	24.82	162	24.65
8	23.37	59	27.29	114	22.65	163F	26.1
9	24.33	60	25	115	24.55	164	26.52
10	25.11	61	25.04	116F	20.71	165	22.71
11	25.32	62	20.93	117F	22.24	166	20.89
12	25.86	63	21.39	119	26.86		
13	26.07	64	23.26	120F	23.84		
14F	22.14	65	21.95	121F	25.74		
15F	22.90	66F	22.26	122	25.1		
17	22.28	67F	21.11	123F	24.77		
18	21.69	68F	19.06	124	22.15		
19	21.01	69F	19.56	127	24.61		
20	26.00	70F	18.61	128	19.53		
21	22.70	71F	18.31	129	28.01		
22F	24.86	72F	20.81	130	26.45		
23F	23.79	73F	21.05	131	24.41		
24F	24.02	74F	17.79	132F	25.51		
25	23.08	75F	20.46	133	23.12		
26	21.37	76	24.19	134	22.33		
27	22.69	78	19.86	135	27.48		
28	26.18	79	23.38	137F	22.89		

  

Spinning Micron Range	
Count	
80s	17.70-19.14
70s	19.15-20.59
64s	20.60-22.04
62s	22.05-23.49
60s	23.50-24.94
58s	24.95-26.39
56s	26.40-27.84
54s	27.85-29.29
50s	29.30-30.99
48s	31.00-32.69

29	24.42	81	20.14	136	25
31	27.13	82F	23.75	138	27.54
32	26.45	83F	20.61	139	26.41
33	25.94	84F	22.24	140F	27.74
36	21.15	85F	23.11	141	26.98
37	22.05	86	22.96	142F	24.49
39	25.24	87	24.32	143	25.25
40	24.35	88	23.76	144F	29.39
43F	23.92	90	26.8	145F	23.87
44F	24.21	92	26.13	146	23.16
45F	24.17	103F	24.55	147F	23.68
51	32.42	104F	23.95	151	20.93