

# ARSBA 2021 Sale Sheep

SampleID	Fiber			Comfort		SampleID	Fiber			Comfort	
	Diameter um	SD um	CVD %	Factor %	Curvature deg/mm		Diameter um	SD um	CVD %	Factor %	Curvature deg/mm
1-498	20.95	4.45	21.2	97.3	105.9	51-6095	21.88	3.56	16.3	98.6	77.8
2-455	20.4	4.05	19.9	97.8	97.4	52-778	22.33	4	17.9	97.3	99.9
3-1982	26.55	4.71	17.7	81.6	95.3	53-643	20.89	3.04	14.6	99.1	120.4
4-2086	24.66	4.1	16.6	92.1	110.9	54-761	23.59	3.95	16.7	96.9	86.3
6-2107	22.68	3.85	17	96.7	115.9	56-2079	21.98	3.66	16.7	98.8	88.3
7-1597	19.94	3.9	19.6	100	86.6	58-2071	24.86	4.8	19.3	87.8	95.4
11-101	23.14	4.79	20.7	93.2	103.1	59-2073	24.35	4.07	16.7	93.5	100.5
16-69	27.16	4.71	17.3	80.3	113.8	60-2144	22.39	3.76	16.8	99.1	116
17-103	23.65	3.43	14.5	96.1	84.3	61-2155	23.2	4.22	18.2	95.6	121.7
19-84	27.47	3.85	14	80.5	96.6	62-1453	21.16	4.03	19	97.2	130.2
20-106	23.53	3.65	15.5	95.8	99.8	63-1429	23.35	3.96	17	96.1	103
21-131	23.38	3.2	13.7	98.4	123.4	65-3327	24.95	4.09	16.4	90.8	99.5
22-9050	21.73	3.23	14.9	98.7	99.2	66-3363	23.01	3.75	16.3	96.3	110.6
23-6122	19.7	4.1	20.8	98.3	91	67-3404	23.67	4.09	17.3	95.2	105.4
24-6123	19.83	3.41	17.2	100	95.6	68-3417	19.82	3.3	16.6	99.5	87.8
25-6124	20.27	3.79	18.7	98.9	81.9	69-9-4	22.43	3.42	15.2	97.9	102.3
26-6126	19.6	3.37	17.2	99.8	92.7	70-8	25.94	5.48	21.1	82.2	104.2
28-1040	21.56	4.93	22.9	95.9	91	78-157	23.48	4.19	17.8	94.1	113.3
29-1086	20.81	2.61	12.5	99.8	94.4	79-224	24.77	3.15	12.7	95.9	104.1
30-2155	20.04	3.76	18.8	100	118.5	80-1018	24.81	5.5	22.2	85	91.5
31-2092	27.88	4.68	16.8	75.5	89	81-1090	21.54	4.82	22.4	96.8	87.9
32-2095	27.7	4.96	17.9	77.1	89.6	82-1198	19.97	3.92	19.6	98.8	86.3
33-1963	31.7	5.11	16.1	42.4	94.2	83-1128	21.09	4.68	22.2	96.4	74.7
34-2086	31.64	4.97	15.7	43.9	73.3	101-2093	22.69	3.77	16.6	97.8	109
35-2080	29.14	5.3	18.2	62	79.1	102-2090	19.69	3.28	16.7	99.3	108.2
36-2134	24.25	3.83	15.8	94.8	85.7	103-3406	21.79	3.75	17.2	97.3	112.3
37-2347	22.72	4.55	20	95	101.4						
38-2345	22.65	4.73	20.9	95.4	94.4						
39-2350	22.42	4.4	19.6	94.5	90.4						
40-113	24.14	3.61	15	95.6	89.2						
41-2318	24.64	3.77	15.3	92.9	123.1						
42-2336	33.29	7.03	21.1	36.8	72.6						
43-025	24.74	3.65	14.8	92.4	105.3						
44-32	22.2	3.83	17.3	97.3	111.1						
45-109	25.8	4.14	16	86.7	100.3						
47-186	20.39	3.92	19.2	98.8	82.7						
48-27	24.42	4.06	16.6	93.3	90.1						
49-32	24.29	3.99	16.4	92.5	84.9						
50-57	23.34	5.21	22.3	90.3	92.5						
<b>Averages:</b>	<b>23.4</b>	<b>4.1</b>	<b>17.6</b>	<b>91.4</b>	<b>98.2</b>						